

**PAT-NO:** JP02006181753A  
**DOCUMENT-IDENTIFIER:** JP 2006181753 A  
**TITLE:** DECORATIVE FILM FOR STEEL SHEET

**PUBN-DATE:** July 13, 2006

**INVENTOR-INFORMATION:**

NAME	COUNTRY
NOGUCHI, KATSUHIRO	N/A
URUSHIBARA, TATSUYA	N/A
AMANO, EIICHI	N/A

**ASSIGNEE-INFORMATION:**

NAME	COUNTRY
OKURA IND CO LTD	N/A

**APPL-NO:** JP2004375400  
**APPL-DATE:** December 27, 2004

**INT-CL-  
ISSUED:**

TYPE	IPC DATE IPC-OLD
IPCP	B32B15/09 20060101 B32B015/09
IPFC	B32B15/08 20060101 B32B015/08
IPFC	B32B27/36 20060101 B32B027/36

**ABSTRACT:**

**PROBLEM TO BE SOLVED:** To provide a decorative film for a steel sheet which is not foamed and has good adhesiveness even if the temperature of the steel sheet at the time of lamination is 220°C, has good durability in boiling water and the good adhesiveness with a coking agent.

**SOLUTION:** The decorative film for the steel sheet is constituted by providing an adhesive layer (A), which is based on an amorphous copolymerized polyethylene terephthalate resin prepared by substituting a part of ethylene glycol being a diol part of polyethylene terephthalate with 1,4-cyclohexane dimethanol, on the steel sheet on the side of the laminating surface with the steel sheet and providing a layer (B), which is based on polybutylene terephthalate compounded with a pigment, on the adhesive layer and characterized in that the thickness of the adhesive layer (A) is 2-50 µm and below 50% of the thickness of all of the layers. This decorative film is preferably used in a unit bath decorative steel sheet. The adding amount of the pigment in the layer (B) is 10-40 wt.% and a surface layer (C), which is composed of 50-90 wt.% of polybutylene terephthalate and 50-10 wt.% of a polyethylene terephthalate resin and contains no pigment, is provided on the layer (B).